

Characteristics of Material

Material L20

μ_i	$\tan \delta / \mu_i$	$\alpha \mu r$	Bm	Br	Hc	Tc	r	d
-	$\times 10^{-6}$	$\times 10^{-6} / ^\circ C$	Gauss	Gauss	Oersted	$^\circ C$	$\Omega - cm$	g / cm^3
2000	6(0.01MHz) 70(0.5MHz)	1	2600	1100	0.1	120	10^7	5.0

